

Standard-program Finished fabric of glass filament

| Technical data | | TGG25 | TGG50 | TGG80 | TGG100 | TGG160 | TGG200 | TGG280 | TGG390 |
|--------------------------|-----------------------------|-------|---------|--------------|----------------|--------------|--------------|--------------|--------------|
| Square weight | DIN 53 854 g/m ² | 24 | 49 | 82 | 105 | 166 | 200 | 280 | 394 |
| Thread count warp | DIN 53 853 je cm | 22 | 23. Mai | 11. Aug | 23. Jun | 11. Aug | 17. Mrz | 7 | 6 |
| Thread count weft | DIN 53 853 je cm | 22 | 18. Mai | 12 | 22. Aug | 12 | 12 | 06. Mai | 06. Jul |
| Warp yarn (EC in µm/tex) | | 5/5,5 | 5/11 | 9/34 | 7/22 | 9/68 | 9/68 | 3x 9/68 | 9/68x5 |
| Weft yarn (EC in µm/tex) | | 5/5,5 | 5/11 | 9/34 | 7/22 | 9/68 | 9/68 | 11/204 | 13/272 |
| Thickness | mm | 0.03 | 0.06 | 0.17 | 0.16 | 0.2 | 0.2 | 0.4 | 0.4 |
| Binding | DIN 61 854 | PW | PW | PW or TW 2/2 | PW or cross TW | PW or TW 2/2 | PW or TW 2/2 | PW or TW 2/2 | PW or TW 2/2 |
| Standard width | cm | 100 | 110 | 100 | 110 | 101 | 127 | 100 | 100 |
| Standard roll length | lfm | 100 | 100 | 100 | 100 | 100 | 100 | 100 | 100 |

this are average values which are subject to the usual production variations

Standard program - further adjustments and widths on request