

Technical data sheet

## AVANTI 2K-Universal putty



**AVANTI 2K-Universal putty** is a white-yellow, flexible putty for the professional use as filler and fine putty in one working step.

It is suitable for FRP, metal, wood, cement a.s.o. for filling of holes and roughnesses – for filling of pre-treated surfaces whilst repairing car body parts, metal surfaces, repair and restoration of wood- or cement surfaces.

### Technical data:

grindable after about 10 to 20 minutes  
drop time at 20°C: about 4 - 5 minutes  
burning point about 33°C  
density at 20°C: 1.66 g/cm<sup>3</sup>  
temperature resistance of the hardened material to about 160°C  
resistant against acids, bases, expanding agents, dissolvent, water and de-icing salts.

### Mixing ratio:

100 portions Universal putty with 2 - 3 portions hardener

### Working instruction:

- ▶ Steel- or aluminum sheets, galvanized resp. zinc-plated must be degreased and ground before use
- ▶ On zinc-plated sheets the putty must dry 1-2 hours before grinding
- ▶ Prevent too much hardener a mix homogeneously.
- ▶ Hardened remains may not be stored in tins
- ▶ Polyester-putty doesn't harden at temperatures below 5°C

### Storage-recommendation:

Protect the product of frost and intensive effect of heat • the storage temperature should be between +15°C and +25°C • the max. shelf life is 12 months at cool and dry storage in unopened condition.